



I-Tera[®] MT Very Low-loss Laminate Material

I-Tera[®] MT laminate materials exhibit exceptional electrical properties which are very stable over a broad frequency and temperature range. I-Tera MT is suitable for many of today's high speed digital and RF/microwave printed circuit designs. I-Tera MT features a dielectric constant (Dk) that is stable between -55°C and +125°C up to 20 GHz. In addition, I-Tera MT offers a lower dissipation factor (Df) of 0.0035 making it a cost effective alternative to PTFE and other commercial microwave and high-speed digital laminate materials.

I-Tera MT laminate materials are currently being offered in both laminate and prepreg form in typical thicknesses and standard panel sizes. This provides a complete materials solution package for high-speed digital multilayer, hybrid, RF/microwave, multilayer and double-sided printed circuit designs. I-Tera MT does not require any special through hole treatments commonly needed when processing PTFE-based laminate materials.

www.isola-group.com/products/i-tera-mt/

ORDERING INFORMATION:

Contact your local sales representative or visit www.isola-group.com for further information.

Isola Group
3100 West Ray Road
Suite 301
Chandler, AZ 85226
Phone: 480-893-6527
Fax: 480-893-1409
info@isola-group.com

Isola Asia Pacific (Hong Kong) Ltd.
Unit 3512 - 3522, 35/F
No. 1 Hung To Road, Kwun Tong,
Kowloon, Hong Kong
Phone: 852-2418-1318
Fax: 852-2418-1533
info.hkg@isola-group.com

Isola GmbH
Isola Strasse 2 D-52348
Düren, Germany
Phone: 49-2421-8080
Fax: 49-2421-808164
info-dur@isola-group.com

High Performance

I-Tera[®] MT Data Sheet

**T_g 200, T_d 360
Dk 3.00, Df 0.0035**

Features

- High Thermal Performance
 - ▶ T_g: 200°C (DSC)
 - ▶ T_d: 360°C (TGA @ 5% wt loss)
 - ▶ Low CTE in the Z-axis – 2.8% (50-260°C)
- T260: >60 minutes
- T288: >60 minutes
- RoHS Compliant
- Electrical Properties
 - ▶ Dk: 3.00
 - ▶ Df: 0.0035
 - ▶ Typical electrical properties over a broad frequency and temperature range per IPC-TM-650-2.5.5.5
- Core Material Standard Availability
 - ▶ Thickness: 0.0025"-0.018", 0.020", 0.030" and 0.060"
 - ▶ Available in full size sheet or panel form
- Prepreg Standard Availability
 - ▶ Roll or panel form
 - ▶ Tooling of prepreg panels available
- Copper Foil Type Availability
 - ▶ Standard HTE Grade 3
 - ▶ RTF (Reverse Treat Foil)
 - ▶ VLP-2 (2 micron)
- Copper Weights
 - ▶ ½, 1 and 2 oz (18, 35 and 70 µm) available
 - ▶ Heavier copper available upon request
 - ▶ Thinner copper foil available upon request
- Glass Fabric Availability
 - ▶ Standard E-glass
 - ▶ Square weave glass fabric available
 - ▶ Spread glass fabric available
- Industry Approvals
 - ▶ UL 94 V-0
 - ▶ UL Qualified - 130 MOT
 - ▶ Non-ANSI
 - ▶ IPC-4103 /17

I-Tera[®] MT Specifications

Property	Typical Values				
	Typical Value	Specification	Units	Test Method	
			Metric (English)	IPC-TM-650 (or as noted)	
Glass Transition Temperature (Tg) by DSC	200	170-200	°C	2.4.24	
Decomposition Temperature (Td) by TGA @ 5% weight loss	360	–	°C	ASTM D3850	
T260	60+	–	Minutes	–	
T288	60+	–	Minutes	–	
CTE, X-, Y-axes	A. Pre-Tg B. Post-Tg	AABUS –	ppm/°C	2.4.41	
Z-axis Expansion (50-260°C)	2.8	–	%	2.4.41	
Thermal Conductivity (-100-250°C)	0.32	–	W/mK	ASTM F433	
Thermal Stress 10 sec @ 288°C (550.4°F)	A. Unetched B. Etched	Pass Pass Visual	Rating	2.4.13.1	
Dk, Permittivity	A. @ 2 GHz B. @ 5 GHz C. @ 10 GHz	3.00 3.00 3.00	±0.05 ±0.05 ±0.05	– – –	Bereskin Stripline Bereskin Stripline Bereskin Stripline
Df, Loss Tangent	A. @ 2 GHz B. @ 5 GHz C. @ 10 GHz	0.0035 0.0035 0.0035	±0.0005 ±0.0005 ±0.0005	– – –	Bereskin Stripline Bereskin Stripline Bereskin Stripline
Volume Resistivity	96/35/90	1.33x10 ⁷	1.0x10 ⁶	MΩ-cm	2.5.17.1
Surface Resistivity	96/35/90	1.33x10 ⁵	1.0x10 ⁴	MΩ	2.5.17.1
Dielectric Breakdown	45.4	–	kV	2.5.6	
Arc Resistance	139	60	Seconds	2.5.1	
Electric Strength	45 (1133)	30 (750)	kV/mm (V/mil)	2.5.6.2	
Comparative Tracking Index (CTI)	2	–	Class (Volts)	UL-746A ASTM D3638	
Peel Strength	1 oz. (38µm) EDC foil	1.0 (5.7)	0.53 (3.0)	N/mm (lb/inch)	2.4.8.3
Flexural Strength	A. Lengthwise direction B. Crosswise direction	TBD TBD	–	lb/inch ²	2.4.4
Tensile Strength	A. Lengthwise direction B. Crosswise direction	TBD TBD	–	lb/inch ²	–
Young's Modulus	A. Grain direction B. Fill direction	TBD TBD	–	ksi	ww
Poisson's Ratio	A. Grain direction B. Fill direction	TBD TBD	–	–	xx
Moisture Absorption	0.01	–	%	2.6.2.1	
Flammability	V-0	–	Rating	UL 94	
Max Operating Temperature	130	UL Cert	°C	–	

The data, while believed to be accurate and based on analytical methods considered to be reliable, is for information purposes only. Any sales of these products will be governed by the terms and conditions of the agreement under which they are sold.

www.isola-group.com/products/i-tera-mt/

The Isola name and logo are registered trademarks of Isola Corp. USA in the USA and other countries. I-Tera is a registered trademark of Isola Corp. USA in the USA. All other trademarks mentioned herein are property of their respective owners. © 2013, Isola Group, All rights reserved.

09/13 DSI-TeraF

